

## V-PRO<sup>™</sup> 32 - STEEL FINISH COATING SYSTEM

Job Name:		Client Name:	
Job Location - City:	State:	Created By:	Date:
Product:	Quote:	Customer Approval:	Date:

## **GALVANIZING - POWDER**

## **SPECIFICATIONS**

**Product Application** - Steel structures and steel components purchased. Use this system for improved performance of paint wear and long term corrosion protection.

Warranty - 3 year adhesion/corrosion

**Zinc Coating** - The product is hot-dip galvanized to the requirements of either the current revision of ASTM A123 (Specification for Zinc Coatings on Iron and Steel Products) or the current revision of ASTM A153 (Specification for Zinc Coating on Iron and Steel Hardware). AASHTO, MILSPEC or International specifications can be accommodated when requested in advance.

**Surface Preparation** - The galvanized surface is prepared for painting by sweep blasting to the current revision of ASTM D6386 requirements utilizing cast steel abrasives conforming to the Society of Automotive Engineers (SAE) Recommended Practice J827. The blast method used is a recirculating, closed cycle centrifugal wheel system with abrasive conforming to SAE Shot Number S280.

**Prime Coat** - High Build Epoxy Powder. Epoxies are used as a primer under various exterior durable top-coats. They add film build, corrosion resistance, chip resistance, and adhesion. They are not color stable when exposed to UV light and must be top-coated for gloss and color retention. The prime coat is applied to an average dry film thickness (DFT) of 5 mils on the bottom 8' of the pole. The average dry film thickness (DFT) is 3 mils above 8' and on the arms.

**Exterior Coating** -TGIC. TGIC powders are very similar to the TGIC Polyesters as far as their use, but offer better exterior gloss and color retention. They can be used as single coat systems over most metal substrates for mild to moderate exposure conditions. They offer good scratch and abrasion resistance.

The exterior coating is applied to an average dry film thickness (DFT) of 3 mils. The coating is electrostatically applied and cured in a gas fired convection oven. The thermosetting powder resin provides adhesion that meets 5A or 5B classifications of ASTM D3359.

The V-PRO 32 finish system is available in 11 standard colors that match the most commonly used colors in the industry. There are thousands of other colors available upon request.

## Standard colors available:

- Black (BK)
- Dark Bronze (DB)
- Medium Bronze (MB)
- White (WH)
- Light Gray (LG)
- Bronze (CB)
- Dark Green (DG)
- Sandstone (ST)
- Hunter Green (HG)
- Slate Gray (SG)
- Silver (SL)



©2018 Valmont Industries, Inc. All rights reserved. Valmont Structures has a policy of continuous product improvement and development. As a result, certain changes in standard equipment, options, price, etc. may have occurred after the publication of this document. Some specifications may not be identical to current production. Valmont Structures reserves the right to change product design and specifications at any time without incurring obligations.